

SIGMAGUARD 240**(SIGMAGUARD TANKSHIELD PRIMER)**

4 pages

September 2005
Revision of January 2003**DESCRIPTION**

two component high solids polyamine cured epoxy primer

PRINCIPAL CHARACTERISTICS

- to be used for ballast tanks (block application or in situ coating)
- outstanding sea water and crude oil resistance
- excellent corrosion resistance
- good resistance against chemically polluted water
- resistant to well designed cathodic protection
- good low temperature drying

COLOURS AND GLOSS

yellow/green - gloss

BASIC DATA AT 20°C(1 g/cm³ = 8.25 lb/US gal; 1 m²/l = 40.7 ft²/US gal)
(data for mixed product)

Mass density

1.4 g/cm³

Volume solids

78 ± 2%

VOC (supplied)

max. 167 g/kg (Directive 1999/13/EC, SED)

max. 239 g/l (approx. 2.0 lb/gal)

Recommended dry film
thickness

125 - 150 µm * in one coat application

Theoretical spreading rate

6.2 m²/l for 125 µm, 5.2 m²/l for 150 µm *

Touch dry after

7 - 8 hours at 5°C, 5 - 6 hours at 10°C, 2 - 3 hours at 20°C

Overcoating interval

min. 7 hours *

max. 28 days *

Curing time

see curing table *

(data for components)

Shelf life (cool and dry place)

at least 12 months

Flash point

base 28°C, hardener 24°C

* see additional data

**RECOMMENDED
SUBSTRATE CONDITIONS
AND TEMPERATURES**

- steel; blast cleaned to a minimum of ISO-Sa2½,
blasting profile (R_z) 40-70 µm
- steel with approved zinc silicate shop primer; sweep blasted to
SPSS-Ss or power tool cleaned to SPSS-Pt3
- previous epoxy coats; dry and free from any contamination and
sufficiently roughened if necessary
- substrate temperature at least 3°C above dew point and free from ice
- maximum relative humidity during application and curing is 85%
- application at temperatures down to -5°C is possible but curing to
hardness takes longer and complete cure will be reached when
temperature increases

SYSTEM SPECIFICATION

marine

system sheet 3106

SIGMAGUARD 240

(SIGMAGUARD TANKSHIELD PRIMER)

September 2005

INSTRUCTIONS FOR USE

mixing ratio by volume: base to hardener 75 : 25

- the temperature of the mixed base and hardener should preferably be above 15°C, otherwise extra solvent may be required to obtain application viscosity
- too much solvent results in reduced sag resistance and slower cure
- thinner should be added after mixing the components

Induction time

none

Pot life

2 hours at 20°C *

* see additional data

AIRLESS SPRAY

Recommended thinner

Sigma thinner 91-92

Volume of thinner

up to 10% for a one coat application of 125 µm dft

Nozzle orifice

approx. 0.53 - 0.64 mm (= 0.021 - 0.025 in)

Nozzle pressure

15 MPa (= approx. 150 bar; 2130 p.s.i.)

AIR SPRAY

Recommended thinner

Sigma thinner 91-92

Volume of thinner

5 - 15% for a one coat application of 125 µm dft

Nozzle orifice

1.8 - 2 mm

Nozzle pressure

0.3 - 0.4 MPa (= approx. 3 - 4 bar, 43 - 57 p.s.i.)

BRUSH/ROLLER

not recommended, only for spot repair and stripe coating

CLEANING SOLVENT

Sigma thinner 90-53

SAFETY PRECAUTIONS

for paint and recommended thinners see safety sheets 1430, 1431 and relevant material safety data sheets

this is a solvent based paint and care should be taken to avoid inhalation of spray mist or vapour as well as contact between the wet paint and exposed skin or eyes

ADDITIONAL DATA

Film thickness and spreading rate

theoretical spreading rate m ² /l	6.2	5.2
dft in µm	125	150

max. dft when brushing:

100 µm

SIGMAGUARD 240

(SIGMAGUARD TANKSHIELD PRIMER)

September 2005

Overcoating table for dft up to 150 µm

substrate temperature	-5°C	5°C	10°C	20°C	30°C
minimum interval	40 hours	20 hours	14 hours	7 hours	4 hours
maximum interval	28 days	28 days	28 days	28 days	14 days

– surface should be dry and free from any contamination

Curing table for dft up to 150 µm

substrate temperature	full cure for immersion in water
-5°C	--
5°C	10 days
10°C	7 days
20°C	3 days
30°C	2.5 days

– adequate ventilation must be maintained during application and curing (please refer to sheet 1433 and 1434)

Pot life (at application viscosity)

15°C	3 hours
20°C	2 hours
30°C	1 hour
40°C	30 min.

Worldwide availability

Whilst it is always the aim of Sigma Coatings to supply the same product on a worldwide basis, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

REFERENCES

Explanation to product data sheets	see information sheet 1411
Safety indications	see information sheet 1430
Safety in confined spaces and health safety	
Explosion hazard - toxic hazard	see information sheet 1431
Safe working in confined spaces	see information sheet 1433
Directives for ventilation practice	see information sheet 1434

SIGMAGUARD 240

(SIGMAGUARD TANKSHIELD PRIMER)

September 2005

LIMITATION OF LIABILITY

The information in this data sheet is based upon laboratory tests we believe to be accurate and is intended for guidance only. All recommendations or suggestions relating to the use of the products made by Sigma Coatings, whether in technical documentation, or in response to a specific enquiry, or otherwise, are based on data which to the best of our knowledge are reliable. The products and information are designed for users having the requisite knowledge and industrial skills and it is the end-user's responsibility to determine the suitability of the product for its intended use.

Sigma Coatings has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Sigma Coatings does therefore not accept any liability arising from loss, injury or damage resulting from such use or the contents of this data sheet (unless there are written agreements stating otherwise).

The data contained herein are liable to modification as a result of practical experience and continuous product development. This data sheet replaces and annuls all previous issues and it is therefore the user's responsibility to ensure that this sheet is current prior to using the product.

The English text of this document shall prevail over any translation thereof.

DS	7400
179161 yellow/green	4009002200